



Temacoat GF Primer

DESCRIPTION

A two-component, polyamide cured epoxy primer containing zinc phosphate.

PRODUCT FEATURES AND RECOMMENDED USES

- Ensures an aesthetically pleasing appearance for epoxy and polyurethane systems.
- Provides excellent adhesion and is used as a primer on steel, aluminium and zinc surfaces.
- Active anti-corrosive pigments ensure corrosion resistance even in severe climatic conditions.
- Recommended for agricultural machinery, haulage equipment and other machinery and equipment.

TECHNICAL DATA

Volume solids 55±2%. (ISO 3233)

Weight solids 70±2%.

Specific gravity 1.4 kg / l (mixed)

Mixing ratio Base 4 parts by volume Temacoat GF Primer
Hardener 1 part by volume 008 5600 or 008 5605 (fast)

Pot life 6 hours (+23°C) with Hardener 008 5600
3 hours (+23°C) with Hardener 008 5605

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
wet	dry	
90µm	50µm	11.0 m ² /l
130µm	70µm	7.8 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 60 µm		0°C	+5°C	+10°C	+23°C	+35°C
Dust dry, after	with Hardener 008 5600	4h	2h	1h	½h	15min
	with Hardener 008 5605	3h	1½h	45min	½h	12min
Touch dry, after	with Hardener 008 5600	22h	11h	5h	2½h	2h
	with Hardener 008 5605	12h	6h	3½h	2h	1½h
Recoatable with epoxy paints, min. after	with Hardener 008 5600	30h	20h	6h	2h	1h
	with Hardener 008 5605	18h	12h	4h	1½h	45min
Recoatable with polyurethane paints, min. after	with Hardener 008 5600	2d	32h	18h	6h	3h
	with Hardener 008 5605	1½d	18h	12h	4h	2h



Temacoat GF Primer

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Gloss Semi-matt.

Color shades Temaspeed Primers colour card. Temaspeed Premium tinting.



Temacoat GF Primer

APPLICATION INSTRUCTIONS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Zinc surfaces: Sweep blast clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Panssaripesu detergent. For hot dip galvanized surfaces see separate application instructions or contact Tikkurila Technical Service.</p> <p>Aluminium surfaces: Sweep blastclean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Maalipesu detergent.</p> <p>Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p>
Recommended primers	Temacoat GF Primer, Temazinc 77, Temazinc 99.
Recommended topcoats	Temacoat HB 30, Temacoat GPL, Temacoat GS 50, Temacoat RM 40, Temacoat GPL-S MIO, Temadur 10, Temadur 20, Temadur 50, Temadur 90, Temadur HB 50, Temadur HB 80, Temadur HS 90, Temathane 50, Temathane 90, Temathane PC 50, Temathane PC 80, Temacryl EA 50.
Application conditions	<p>All surfaces must be clean, dry and free from contamination. The temperature of the ambient air, surface and paint should not fall below +5°C during application and drying. Relative humidity of the air should not exceed 80% during application and drying. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.</p> <p>Note! There is a natural tendency of this coating to chalk, discolor or yellow unevenly. It is recommended to use polyurethane topcoat when there are high aesthetical requirements on color appearance.</p>
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.
Application	<p>For airless spraying, the product is thinned approximately 5–20%. Recommended nozzle tip is 0.011"–0.017" and pressure 120–180 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For brush application the product should be thinned according to the circumstances.</p>
Thinners	Thinner 1031
Cleaning of equipment	Thinner 1031
VOC	The Volatile Organic Compounds amount is 420 g/litre of paint mixture. VOC content of paint mixture (thinned 20% by) volume is 495 g/l.



Temacoat GF Primer

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial and professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

